


## Properties

	<b>Description</b> Full grain, semi-aniline leather	<b>Thickness</b> 1.4mm +/- 0.1mm	<b>Grain Characteristics</b> Smooth – Slightly Pronounced
	<b>Hide Size</b> 55.00 sq. ft. avg.	<b>Weight</b> 3.50oz +/- 0.25oz per sq. ft.	<b>Finish Characteristics</b> Medium – Moderate Traffic Suitable

## Test Performance

**AATCC Method 16, Option E  
Light Fastness**  
Class 4-5 (72 hours)

**ASTM D-2097 Newark Flex:**  
70,000 cycles

**ASTM D-2208 Breaking Force**  
150 lbs.

**ASTM D-4705 Stitch Tear**  
25 lbs.

**ASTM D-5053 Crock Fastness**  
Class 2-3 (dry rub)  
Class 4 (wet rub)

**ASTM D-3884 Abrasion Resistance**  
1,000+ cycles (CS-10)

**ASTM D-4705 Stitch Tear**  
25 lbs.

## Flame Resistance

**California TB 117**  
Complies

**Boston Fire Code BFD-IX-1**  
Complies (with flame treatment)

**NFPA-260 Cigarette Ignition**  
Class I

**ASTM E84 Surface Burning  
Characteristics**  
Class I (with flame treatment)

**FMVSS 302**  
Complies

**FAR 25.853 (a) Am. 25-116,  
App. F, Part I (a)(1)(i)**  
Complies (with flame treatment)

**FAR 25.853 (a) Am. 25-116,  
App. F, Part I (a)(1)(ii)**  
Complies (with flame treatment)

**FAR 25.853 (c) Am. 25-116,  
App. F, Part II (a)(4) and (5)**  
Complies (with flame treatment)

## Notes

Pearlescence may be flame treated to meet most flammability regulations.

Most leathers have been successfully used in California TB 133 applications with suitable fire backers.

The medium finish on Pearlescence makes it suitable for moderate traffic areas.

Call GARRETT at 1-800-342-7738 for samples or more information.

### Showrooms

Atlanta	New York
Charlotte	Philadelphia
Chicago	Raleigh
Cincinnati	San Diego
Dallas	San Francisco
Honolulu	Scottsdale
Houston	Seattle
Laguna Niguel	Troy
Los Angeles	Washington DC

### International

Auckland  
Dubai  
Greece  
Hong Kong  
London  
Paris  
Switzerland  
Sydney



1360 Niagara Street  
Buffalo, New York 14213  
800.342.7738 / 716.882.9301  
Fax 716.882.9358

[www.garrettleather.com](http://www.garrettleather.com)